





Tangra[™]S Pro HD 435-450W

N-type high density bifacial double glass mono module



Bifacial technology enables additional energy harvesting from rear side (up to 30%)



30-year lifespan delivers 10-30% more power compared with conventional P-type modules



The natural lack of LID in the N-type solar cell can increase power generation



Excellent low irradiance performance



Better light trapping and current collection to improve module power output and reliability



Industry-leading, lowest thermal coefficient



Optimized electrical design and lower operating current for reduced hot spot loss and better temperature



Certified to withstand 2400 Pa of wind load and 5400 Pa of snow load



100% triple EL test, which greatly reduces the hidden cracks rate

WARRANTY INSURANCE













^{*} Optional performance warranty insurance. Please contact our local sales staff for more information.



LINEAR PERFORMANCE WARRANTY



COMPREHENSIVE CERTIFICATES



ISO 9001: Quality Management System

ISO 14001: Environmental Management System Standard

ISO 45001: International Occupational Health and

Safety Assessment System Standard

SA8000: 2014 Social Accountability Management System

^{*} Different markets have different certification requirements.

Also, the products are under rapid innovation.

Please confirm the certification status with regional sales representatives.

ELECTRICAL CHARACTERISTICS



Model of modules	SS-BG435-48MDH-G11(T)		SS-BG440-48MDH-G11(T)		SS-BG445-48MDH-G11(T)		SS-BG450-48MDH-G11(T)	
	STC	NOCT	STC	NOCT	STC	NOCT	STC	NOCT
Maximum power — P _{mp} (W)	435	327	440	331	445	335	450	338
Open-circuit voltage — V _{oc} (V)	34.49	32.77	34.67	32.94	34.85	33.11	35.03	33.28
Short-circuit current — I _{sc} (A)	15.90	12.84	15.95	12.88	16.00	12.92	16.05	12.96
Maximum power voltage − V _{mp} (V)	29.54	27.51	29.72	27.68	29.90	27.88	30.08	27.96
Maximum power current — I _{mp} (A)	14.73	11.89	14.81	11.96	14.89	12.02	14.97	12.09
Module efficiency $-\eta_m$ (%)	21.8		22.0		22.3		22.5	

STC (Standard Testing Conditions): Irradiance 1000W/m², Cell Temperature 25 °C , Spectra at AM1.5

NOCT (Nominal Operating Cell Temperature): Irradiance 800W/m², Ambient Temperature 20°C, Spectra at AM1.5, Wind at 1m/s

ELECTRICAL CHARACTERISTICS WITH DIFFERENT POWER BIN (REFERENCE TO 13.5% IRRADIANCE RATIO)

Peak Power (P _{max}) (W)	482	488	493	499
Open Circuit Voltage (V _{oc}) (V)	34.49	34.67	34.85	35.03
Short Circuit Current (I _{sc}) (A)	17.62	17.67	17.73	17.78
36 ()				
- '				
MPP Voltage (V_{mp}) (V) MPP Current (I_{mp}) (A)	29.54	29.72 16.41	29.90 16.50	30.08 16.59

STRUCTURAL CHARACTERISTICS

Module size (L*W*H)	1762 x 1134 x 30 mm
Weight	24.3 kg
Cell	96 cells, N-type monocrystalline
Front glass	2.0mm, anti-reflection coating
Back glass	2.0mm, heat strengthened glass
Frame	Anodized aluminum alloy (Silver/Black)
Junction box	IP68, 3 diodes
Output wire	4.0 mm ²
Wire length	300mm/1200mm/customized
Connector	MC4 Compatible
Packing Specification	36pcs/pallet; 936 pcs/40'HQ


OPERATING PARAMETERS

Power tolerance (W)	(0,+5)
Maximum system voltage (V)	1500
Maximum rated fuse current (A)	30
Current operating temperature (°C)	-40~+85 °C
Mechanical load	5400 Pa∗/ 2400 Pa⊗


TEMPERATURE PERFORMANCE RATINGS


TANGRA temperature coefficient (P _{max})	-0.30 %/°C
Temperature coefficient (V _{oc})	-0.28 %/°C
Temperature coefficient (I_{sc})	+0.04 %/°C
Nominal operating cell temperature	43±2 ℃


MODULE DIMENSIONS (MM)











 $^{^{\}star}$ The unmarked tolerance is $\pm 1~\text{mm}$ Length shown in mm





Web: www.sunovathornova.com

E-mail: info@sunova-solar.com

* The technical parameters contained in this data sheet may exhibit variations contingent upon the region. Sunova Solar and Thornova Solar do not guarantee their full accuracy. Due to continuous innovation, research, development and products improvements, Sunova Solar and Thornova Solar reserve the right to adjust the information in this data sheet at an incorporate it as an intrinsic component of the legally binding agreement ratified by both parties. The Chinese (or any other language) translation of this data sheet is for reference only. If there is any discrepancy between the English version and the Chinese version for other language versions), the English version shall prevail.

Make it happen! SD202406001EN